

Appl. No. 10/648,429

Attorney Docket No. 81872.0050

Amtd. Dated June 23, 2006

Customer No. 26021

Reply to Notice of Non-Compliant Amendment of June 5, 2006

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently amended) A dry etching method for fabricating a substrate, comprising:

placing the substrate on an RF electrode in a chamber;

placing a plate to cover the substrate, the plate being provided with a number of opening portions in a central region thereof and a number of opening portions in a peripheral region surrounding the central region thereof, an open area ratio of the opening portions in ~~a the peripheral portion side of the plate~~ region being smaller than an open area ratio of the opening portions in ~~a the central portion region~~.

2. (Previously presented) The dry etching method according to Claim 1, wherein:

the plate is placed to be spaced apart from the surface of the substrate by 5 to 30 mm.

3. (Previously presented) The dry etching method according to Claim 1, wherein:

the substrate is a plate or a film member made of one material selected from silicon, glass, metal, plastic, and resin.

4. (Previously presented) The dry etching method according to Claim 1, wherein:

the dry etching method is a reactive ion etching method.

5-7. (Canceled)

App'l. No. 10/648,429

Attorney Docket No. 81872.0050

Am't. Dated June 23, 2006

Customer No. 26021

Repl'y to Notice of Non-Compliant Amendment of June 5, 2006

8. (Currently amended) A dry etching method for fabricating a substrate, comprising:

placing the substrate on an RF electrode in a chamber;

placing a plate to cover the substrate while securing a distance from the surface of said substrate, the plate being provided with a number of opening portions, each opening portion being of a size such that allows a virtual column having a diameter equal to or less than half (1/2) the distance to pass through the opening portion while inhibiting a virtual column having a diameter greater than half the distance from passing through the opening portion;

~~introducing a gas inside said chamber.~~

9. (Previously presented) The dry etching method according to Claim 8, wherein:

the plate is placed to be spaced apart from the surface of the substrate by 5 to 30 mm.

10. (Previously presented) The dry etching method according to Claim 8, wherein:

the dry etching method is a reactive ion etching method.

11-14. (Canceled)

15. (Currently amended) A dry etching method for fabricating a substrate comprising:

placing the substrate on an RF electrode in a chamber;

Appl. No. 10/648,429

Attorney Docket No. 81872.0050

Amdt. Dated June 23, 2006

Customer No. 26021

Repl.y to Notice of Non-Compliant Amendment of June 5, 2006

placing a plate to cover the substrate, said plate being provided with a number of opening portions, chamfered portions being provided to the top and/or bottom corners of the opening portions.

16-20. (Canceled)

21. (Currently amended) A dry etching method for fabricating a substrate, comprising:

placing the substrate on an RF electrode in a chamber;

placing a plate to cover the substrate, the plate being provided with a number of opening portions in a central region thereof and a number of opening portions in a peripheral region surrounding the central region thereof, an open area ratio of the opening portions in a the peripheral portion side of the plate region being smaller than an open area ratio of the opening portions in a the central portion region;

wherein a number of compounds are formed by an etching of the substrate during an RF power applying, wherein the compounds are trapped in a space between the substrate and the plate.

22. (Previously presented) The dry etching method according to claim 21, wherein:

the plate is placed to be spaced apart from the surface of the substrate by 5 to 30 mm.

Appl. No. 10/648,429

Attorney Docket No. 81872.0050

Amdt. Dated June 23, 2006

Customer No. 26021

Reply to Notice of Non-Compliant Amendment of June 5, 2006

23. (Previously presented) The dry etching method according to claim 21, wherein:

the substrate is a plate or a film member made of one material selected from silicon, glass, metal, plastic and resin.

24. (Previously presented) The dry etching method according to claim 21, wherein

the dry etching method is a reactive ion etching method.

25. (Currently amended) A dry etching method for fabricating a substrate, comprising:

placing the substrate on an RF electrode in a chamber;

placing a plate to cover the substrate, the plate being provided with a number of opening portions in a central region thereof and a number of opening portions in a peripheral region surrounding the central region thereof, an open area ratio of the opening portions in a the peripheral portion-side-of-the-plate region being smaller than an open area ratio of the opening portions in a the central portion region;

wherein a number of compounds are formed by an etching of the substrate during an RF power applying, wherein the compounds are attached to the surface of the substrate.

26. (Previously presented) The dry etching method according to claim 25, wherein

the plate is placed to be spaced apart from the surface of the substrate by 5 to 30 mm.

27. (Previously presented) The dry etching method according to claim 25, wherein

Appl. No. 10/648,429

Attorney Docket No. 81872.0050

Am.dt. Dated June 23, 2006

Customer No. 26021

Reply to Notice of Non-Compliant Amendment of June 5, 2006

the substrate is a plate or a film member made of one material selected from silicon, glass, metal, plastic and resin.

28. (Currently amended) The dry etching method according to claim 29 1, wherein comprising introducing a gas in a chamber; and

~~the dry etching method is a reactive ion etching method~~ applying an RF power supply to said RF electrode.

29. (Currently amended) The dry etching method according to claim ~~1~~ 28, comprising introducing a gas in a chamber; and wherein

~~applying an RF power supply to said RF electrode~~ the dry etching method is a reactive ion etching method.

30. (Previously presented) The dry etching method according to claim 8, comprising introducing a gas in a chamber; and

applying an RF power supply to said RF electrode.

31. (Previously presented) The dry etching method according to claim 15, comprising

introducing a gas in a chamber; and

applying an RF power supply to said RF electrode.

32. (New) The dry etching method according to claim 1, wherein the central region of the plate is opposed to a central region of the substrate, and the peripheral region of the plate is opposed to a peripheral region of the substrate.